

# Technical Information

## Chemical Resistance – Enclosure Material

### KEY:

- S** = Superior Resistance/Completely Unaffected under all Conditions
- L** = Limited Resistance, Some Chemical Attack May Occur Over Time
- M** = Moderate Resistance, Superficial Effects only, Testing Recommended
- U** = Unsatisfactory, Severe/Chemical Attack in a relatively short time
- = No Data Available

**TABLE 3. CHEMICAL RESISTANCE OF ENCLOSURE MATERIALS**

CHEMICAL	ALUMINUM	FIBER GLASS POLYESTER	STEEL			STAINLESS STEEL		PC	PVC
			POLYESTER POWDER	URETHANE ENAMEL	GALVANIZED	TYPE 304	TYPE 316		
Acetyldehyde	S	U	–	–	–	S	S	U	U
Acetic Acid (10%)	L	S	U	U	U	S	U	S	U
Acetone	S	L	L	U	L	S	S	U	U
Aluminum Chloride (10%)	U	S	U	U	U	U	M	S	S
Aluminum Sulfate (10%)	L	S	U	U	U	U	S	S	S
Ammonia Gas	L	S	–	–	–	S	S	–	–
Ammonium Chloride	U	S	U	U	U	S	S	S	S
Ammonium Hydroxide (10%)	S	L	U	U	U	S	S	U	S
Ammonium Nitrate (10%)	M	S	U	U	U	S	S	U	S
Ammonium Phosphate (10%)	L	M	S	L	U	S	M	S	–
Ammonium Sulfate	S	S	–	–	–	S	S	S	S
Aniline	L	U	–	–	–	S	S	U	L
ASTM #1 Oil	S	S	S	S	S	S	S	L	–
ASTM #3 Oil	S	S	S	S	S	S	S	L	–
Axle Grease	S	S	S	S	S	S	S	L	–
Benzene	S	S	–	–	S	S	S	U	L
Boric Acid (10%)	M	S	U	U	U	S	S	S	L
Bromine	U	L	U	U	U	U	U	U	U
Butyl Acetate	M	L	–	–	–	S	S	U	U
Butyric Acid	U	S	–	–	–	S	S	U	U
Calcium Chloride (10%)	L	S	U	U	U	L	S	S	L
Calcium Hydroxide (10%)	U	S	U	U	U	S	S	S	L

## Chemical Resistance – Enclosure Material

TABLE 3. CONTINUED									
CHEMICAL	ALUMINUM	FIBER GLASS POLYESTER	STEEL			STAINLESS STEEL		PC	PVC
			POLYESTER POWDER	URETHANE ENAMEL	GALVANIZED	TYPE 304	TYPE 316		
Calcium Hypochlorite (10%)	L	M	U	U	U	U	M	L	L
Calcium Sulfate	M	S	U	U	U	S	S	S	L
Carbolic Acid (25%)	M	L	U	U	U	S	S	U	
Carbon Disulfide	S	L	—	—	—	S	S	U	U
Carbon Tetrachloride	S	M	U	S	S	U	S	U	
Chlorine (dry)	S	S	—	—	—	S	S	U	U
Chlorine (water) 5-10 ppm	M	L	S	U	U	U	—	S	S
Chlorobenzene	S	S	—	—	S	S	S	U	
Chloroform	L	U	—	—	—	S	S	U	U
Chrome Plating Solution	U	L	U	U	U	L	L	S	—
Chromic Acid	S	S	—	—	—	U	U	U	U
Citric Acid (10%)	U	M	U	U	U	S	S	S	L
Copper Sulfate	U	S	—	—	—	S	S	S	S
Creosote	L	L	—	—	—	S	S	U	—
Cutting Fluid (5 Star) 10%	S	S	U	U	U	S	S	L	—
Cutting Fluid (Castrol 980 H)	S	S	S	U	U	S	S	L	—
Cutting Fluid (Norton 205)	U	S	U	U	U	S	S	S	—
Cutting Fluid (Rustlick) 10%	M	S	U	U	U	S	S	S	—
Cutting Oil (Dark)	S	S	S	S	S	S	S	S	—
Diethyl Ether	S	S	—	—	—	S	S	U	U
Ethyl Alcohol	S	S	M	U	S	S	S	M	S
Ethylene Dichloride	S	L	—	—	—	—	—	U	U
Ethylene Glycol	S	S	S	S	U	S	S	S	S
Ferric Chloride	U	S	U	U	U	S	U	S	S
Ferric Nitrate	—	S	—	—	—	S	S	S	S
Ferric Sulfate	M	S	—	—	—	S	S	S	S
Fluorine	S	U	—	—	—	M	—	L	U
Formaldehyde	S	S	—	—	—	L	S	S	L
Formic Acid	U	S	U	U	U	M	S	S	—
Fuel Oil (#2)	S	S	M	S	S	S	M	L	S
Gasoline	S	M	—	—	—	S	S	U	S
Glycerine	S	S	—	—	S	S	S	S	S
Hydraulic Brake Fluid	S	S	U	U	S	S	S	U	—
Hydraulic Oil	S	S	S	S	S	S	S	L	S

# Technical Information

## Chemical Resistance – Enclosure Material

TABLE 3. CONTINUED

CHEMICAL	ALUMINUM	FIBER GLASS POLYESTER	STEEL			STAINLESS STEEL		PC	PVC
			POLYESTER POWDER	URETHANE ENAMEL	GALVANIZED	TYPE 304	TYPE 316		
Hydrochloric Acid (10%)	U	M	U	U	U	U	U	S	S
Hydrocyanic Acid	S	U	—	—	—	S	S	L	L
Hydrofluoric Acid (20%)	U	U	U	U	U	U	U	L	L
Hydrogen Peroxide	S	M	—	—	—	L	S	S	S
Hydrogen Sulfide	M	S	—	—	—	L	S	L	L
Hypochlorous Acid	U	S	—	—	—	—	—	—	—
Isopropyl Alcohol	S	S	M	U	S	S	S	S	—
Kerosene	S	S	S	S	S	S	S	L	S
Lacquer Thinner	S	S	L	U	S	S	S	U	U
Lactic Acid	M	S	—	—	—	L	S	L	L
Lime	M	M	—	—	—	—	—	—	L
Liquid Dish Soap (10%)	M	S	U	U	U	S	M	S	S
Lubricating Oils	S	S	—	—	—	S	S	S	—
Magnesium Chloride (10%)	L	S	U	U	U	S	S	S	L
Magnesium Hydroxide (10%)	L	S	U	U	U	S	S	S	S
Mercuric Chloride (10%)	U	M	U	U	U	S	U	S	L
Methyl Ethyl Ketone	S	L	—	—	—	S	S	U	U
Methylene Chloride	S	S	U	U	M	S	S	U	U
Milk	S	S	—	—	—	S	S	S	S
Mineral Oil	S	S	—	—	—	S	S	S	S
Mineral Spirits	S	S	S	S	S	S	S	L	S
Motor Oil (10 weight)	S	S	S	S	S	S	S	S	L
Nickel Salts	L	S	—	—	—	L	S	S	S
Nitric Acid (10%)	U	M	U	U	U	S	S	L	S
Nitrobenzene	S	L	—	—	—	S	S	U	U
Oleic Acid	S	S	—	—	—	L	S	S	L
Perchlorethylene	S	S	S	U	S	S	S	U	L
Phosphoric Acid (25%)	U	L	U	U	U	S	S	S	S
Phosphoric Acid (50%)	U	U	U	U	U	S	S	S	S
Pickling Solution	U	M	U	U	U	S	M	S	—
Potassium Carbonate (10%)	U	S	S	S	L	S	S	S	L
Potassium Chloride (25%)	L	S	U	U	U	S	S	S	S
Potassium Hydroxide (25%)	U	U	U	U	U	M	M	U	S
Potassium Nitrate (10%)	U	S	U	U	U	S	S	S	S

## Chemical Resistance – Enclosure Material

TABLE 3. CONTINUED									
CHEMICAL	ALUMINUM	FIBER GLASS POLYESTER	STEEL			STAINLESS STEEL		PC	PVC
			POLYESTER POWDER	URETHANE ENAMEL	GALVANIZED	TYPE 304	TYPE 316		
Potassium Sulfate (10%)	L	S	U	U	U	S	S	S	L
Soap (Igepal) 10%	L	S	S	U	U	S	S	S	S
Sodium Bicarbonate (10%)	L	S	S	S	U	S	S	S	S
Sodium Bisulfate (10%)	U	L	U	U	U	S	S	S	S
Sodium Chloride (25%)	L	S	U	U	U	S	S	S	S
Sodium Hydroxide	U	U	U	U	U	M	M	U	S
Sodium Hypochlorite	U	M	U	U	U	S	M	L	S
Sodium Nitrate (10%)	M	S	U	U	U	S	S	S	S
Sodium Phosphate (10%)	L	S	U	U	U	S	S	S	S
Sulfuric Acid (25%)	U	S	U	U	U	S	S	S	S
Sulfurus Acid (10%)	U	U	U	U	U	S	S	S	S
Tannic Acid ((10%)	L	S	U	U	U	M	M	S	S
Tetrahydrofuran	M	L	U	U	U	S	S	U	U
Toluene	S	S	L	U	S	S	S	U	U
Trichloroethylene	S	U	—	—	—	L	S	U	U
Trisodium Phosphate	L	M	—	—	—	—	—	S	S
Turpentine	S	M	M	U	L	S	S	S	U
Vegetable Oils	S	S	—	—	—	S	S	S	S
Vinegar	M	S	—	—	—	S	S	S	L
Water, Industrial	L	S	L	L	L	S	S	S	S
Water, Rain	L	S	S	L	L	S	S	S	—
Water, Sea	L	S	U	U	U	S	S	S	S
Water, Tap	L	S	S	L	L	S	S	S	S
Xylene	S	S	L	U	S	S	S	U	U
Zinc Acetate	S	S	—	—	—	S	S	—	—
Zinc Chloride	L	S	S	U	U	M	S	M	L
Zinc Sulfate	S	S	—	—	—	M	S	S	S

Sources: Robroy Industries Reagent Testing Lab, Corrosion Resistant Materials Handbook, 4th Edition, Noyes Data Corp., Raw Material Vendors

# Technical Information

## Chemical Resistance – Gaskets, Windows and Other

**TABLE 4. SPECIFIC CHEMICAL RESISTANCE INFORMATION  
OTHER MATERIALS USED FOR ENCLOSURE FEATURES**

CHEMICAL	RIGID PVC	GLASS NYLON	GASKETS			WINDOWS	
			NEOPRENE RUBBER	SILICONE RUBBER	URETHANE	ACRYLIC	POLY CARBONATE
Acetyldehyde	U	—	S	S	—	—	—
Acetic Acid (10%)	L	U	U	M	L	S	S
Acetone	U	S	U	S	U	U	U
Aluminum Chloride (10%)	S	U	S	S	S	S	S
Aluminum Sulfate (10%)	S	L	U	S	S	S	S
Ammonia Gas	—	S	S	S	—	S	—
Ammonium Chloride	S	U	S	S	S	S	S
Ammonium Hydroxide (10%)	S	—	L	L	S	S	U
Ammonium Nitrate (10%)	S	U	U	S	S	S	U
Ammonium Phosphate (10%)	—	L	U	S	S	S	S
Ammonium Sulfate	S	U	S	S	—	—	—
Aniline	S	L	U	U	—	S	—
ASTM #1 Oil	—	—	M	S	S	S	M
ASTM #3 Oil	—	—	U	L	S	S	M
Axle Grease	—	—	L	S	S	S	M
Benzene	U	S	U	U	—	U	—
Boric Acid (10%)	L	S	S	S	S	S	S
Bromine	U	U	U	U	U	L	U
Butyl Acetate	U	S	U	U	—	U	—
Butyric Acid	U	U	U	—	—	—	—
Calcium Chloride (10%)	S	U	S	S	S	S	S
Calcium Hydroxide (10%)	S	—	U	S	L	S	S
Calcium Hypochlorite (10%)	S	U	U	S	U	M	S
Calcium Sulfate	S	U	S	S	S	S	S
Carbolic Acid (25%)	—	—	U	U	U	U	U
Carbon Disulfide	U	—	U	—	—	S	—
Carbon Tetrachloride	L	S	U	U	U	S	U
Chlorine (dry)	L	—	—	—	—	—	—
Chlorine (water) 5-10 ppm	L	—	L	S	S	S	S
Chlorobenzene	U	S	U	U	—	L	—
Chloroform	U	U	U	U	—	U	—
Chrome Plating Solution	—	—	U	U	U	S	S
Chromic Acid	L	U	U	M	—	U	—
Citric Acid (10%)	S	L	U	S	U	S	S

## Chemical Resistance – Gaskets, Windows and Other

**TABLE 4. CONTINUED**

CHEMICAL	RIGID PVC	GLASS NYLON	GASKETS			WINDOWS	
			NEOPRENE RUBBER	SILICONE RUBBER	URETHANE	ACRYLIC	POLY CARBONATE
Copper Sulfate	S	L	S	S	—	U	—
Creosote	—	U	U	U	—	—	—
Cutting Fluid (5 Star) 10%	—	—	U	S	S	S	M
Cutting Fluid (Castrol 980 H)	—	—	L	S	S	S	L
Cutting Fluid (Norton 205)	—	—	S	S	S	S	S
Cutting Fluid (Rustlick) 10%	—	—	S	S	S	S	S
Cutting Oil (Dark)	—	—	U	S	S	S	S
Diethyl Ether	U	—	—	U	—	U	—
Ethyl Alcohol	S	—	L	S	S	U	M
Ethylene Dichloride	U	—	U	U	—	U	—
Ethylene Glycol	S	—	S	S	S	S	S
Ferric Chloride	S	U	L	S	L	S	S
Ferric Nitrate	S	U	S	M	—	—	—
Ferric Sulfate	S	U	S	M	—	—	—
Fluorine	L	—	—	U	—	—	—
Formaldehyde	L	U	U	M	—	S	—
Formic Acid	L	S	U	L	L	U	S
Fuel Oil (#2)	S	—	U	U	U	S	S
Gasoline	S	S	U	L	—	S	—
Glycerine	S	S	S	S	—	S	—
Hydraulic Brake Fluid	—	—	U	S	U	U	U
Hydraulic Oil	—	—	U	S	S	S	M
Hydrochloric Acid (10%)	S	U	L	L	U	S	S
Hydrocyanic Acid	S	—	S	M	M	—	—
Hydrofluoric Acid (20%)	L	U	U	U	—	S	M
Hydrogen Peroxide	S	U	U	M	—	S	—
Hydrogen Sulfide	S	—	U	M	—	—	—
Hypochlorous Acid	—	—	—	—	—	—	—
Isopropyl Alcohol	—	—	S	S	S	S	S
Kerosene	S	—	U	U	S	S	M
Lacquer Thinner	—	S	U	S	L	U	U
Lactic Acid	S	L	L	—	—	L	—

# Technical Information

## Chemical Resistance – Gaskets, Windows and Other

TABLE 4. CONTINUED

CHEMICAL	RIGID PVC	GLASS NYLON	GASKETS			WINDOWS	
			NEOPRENE RUBBER	SILICONE RUBBER	URETHANE	ACRYLIC	POLY CARBONATE
Lime	—	—	S	M	—	—	—
Liquid Dish Soap (10%)	S	—	L	S	S	S	S
Lubricating Oils	—	—	U	U	—	S	—
Magnesium Chloride (10%)	S	S	S	S	S	S	S
Magnesium Hydroxide (10%)	S	—	S	S	S	S	S
Mercuric Chloride (10%)	L	—	U	L	U	S	S
Methyl Ethyl Ketone	U	S	S	U	—	L	—
Methylene Chloride	—	U	U	S	U	U	U
Milk	S	—	S	S	—	S	—
Mineral Oil	S	—	L	M	—	S	—
Mineral Spirits	—	—	U	U	S	S	M
Motor Oil (10 weight)	—	—	U	U	S	S	S
Nickel Salts	S	—	U	S	—	—	—
Nitric Acid (10%)	S	U	U	U	U	S	L
Nitrobenzene	U	S	U	—	—	—	—
Oleic Acid	S	U	—	U	—	—	—
Perchloroethylene	—	—	U	S	U	U	U
Phosphoric Acid (25%)	S	U	S	S	U	S	S
Phosphoric Acid (50%)	S	U	S	S	U	S	S
Pickling Solution	—	—	L	M	M	S	S
Potassium Carbonate (10%)	L	S	S	S	S	S	S
Potassium Chloride (25%)	S	L	S	S	S	S	S
Potassium Hydroxide (25%)	S	S	U	L	M	U	U
Potassium Nitrate (10%)	S	L	S	S	S	S	S
Potassium Sulfate (10%)	SL	S	S	S	S	S	S
Soap (Igepal) 10%	S	—	U	S	S	S	S
Sodium Bicarbonate (10%)	S	S	S	S	S	S	S
Sodium Bisulfate (10%)	S	L	S	S	L	S	S
Sodium Chloride (25%)	S	S	S	S	S	S	S
Sodium Hydroxide	S	S	U	U	M	S	U
Sodium Hypochlorite	S	U	U	S	U	S	S
Sodium Nitrate (10%)	S	S	S	S	S	S	S

## Chemical Resistance – Gaskets, Windows and Other

TABLE 4. CONTINUED							
CHEMICAL	RIGID PVC	GLASS NYLON	GASKETS			WINDOWS	
			NEOPRENE RUBBER	SILICONE RUBBER	URETHANE	ACRYLIC	POLY CARBONATE
Sodium Phosphate (10%)	S	—	U	S	S	S	S
Sulfuric Acid (25%)	S	U	S	S	U	S	S
Sulfuric Acid (10%)	S	—	U	U	L	S	S
Tannic Acid ((10%)	S	U	U	L	U	S	S
Tetrahydrofuran	—	S	U	U	U	U	U
Toluene	U	S	U	U	U	U	U
Trichloroethylene	U	U	U	U	—	U	—
Trisodium Phosphate	S	—	—	—	—	—	—
Turpentine	—	S	U	L	U	S	S
Vegetable Oils	S	—	L	S	—	S	—
Vinegar	—	S	L	S	—	S	—
Water, Industrial	S	—	S	S	S	S	S
Water, Rain	S	—	S	S	S	S	S
Water, Sea	S	—	S	S	S	S	S
Water, Tap	S	—	S	S	S	S	S
Xylene	—	S	U	M	U	S	U
Zinc Acetate	—	—	—	U	—	—	—
Zinc Chloride	S	U	M	S	U	S	M
Zinc Sulfate	S	L	S	S	—	—	—

Sources: Robroy Industries Reagent Testing Lab, Corrosion Resistant Materials Handbook, 4th Edition, Noyes Data Corp., Raw Material Vendors